

台灣塑膠工業股份有限公司麥寮廠 中華民國臺灣省雲林縣麥寮鄉台塑工業園區1號

Formosa Plastics Corporation

## Technical Data Sheet Taisox 7350M

## 1.Product description

7350M are an ethylene/vinylene acetate copolymer. The trade name is Taisox. This product manufactured by the high-pressure process. By incorporating vinyl acetate (VA) into the ethylene chain produce co-polymerization to EVA.

7350M are a general-purpose for X-linked foam shoes, mid-sole, gaskets. It provides good chemical resistance, excellent elasticity, and high flexible properties.

## 2. Typical properties

Units	Test Method	Typical Value
g/10min	ASTM D1238	2.5
g/cm <sup>3</sup>	ASTM D1505	0.938
%	FPC method	18
°C	DSC	84
°C	ASTM D746	<-70
°C	ASTM D1525	60
	·	• 
Kg/cm <sup>2</sup>	ASTM D638	45
Kg/cm <sup>2</sup>	ASTM D638	150
%	ASTM D638	800
Shord A	ASTM D2240	88
Shord D	ASTM D2240	38
	g/10min g/cm <sup>3</sup> % °C °C °C °C Kg/cm <sup>2</sup> Kg/cm <sup>2</sup> % Shord A	g/10min ASTM D1238 g/cm <sup>3</sup> ASTM D1505 % FPC method °C DSC °C ASTM D746 °C ASTM D746 °C ASTM D1525 Kg/cm <sup>2</sup> ASTM D638 Kg/cm <sup>2</sup> ASTM D638 % ASTM D638

\*Data shown are average values and should not be examined for specifications